



Decorative Concrete Technology

## A Few Simple Steps for Error-Free Results and Increased Profits!



- ◆ Spray or Roll on after sweat finish.
- ◆ Pigmented for easy view of coverage.
- ◆ Surface is rain safe in 2 hours.
- ◆ Needs no plastic sheeting.

Easy to Apply...



- ◆ Rinse to expose surface within 24 hours.
- ◆ Hose off the same day or Pressure wash following day.

Easy to Remove....



- ◆ Using Integral Color adds enhancement.
- ◆ Seal and protect the surface using Increte's Cure-Crete cure and seal.

Consistent Results.

# SURE ETCH

## CONCRETE SURFACE RETARDERS

### SELECT YOUR SURFACE FINISH

Increte Surface Retarders are available in 4 standard finishes ranging from Micro-Etch to Fully Exposed Aggregate.

Choice of grade is based on the aggregate size to expose and the strength of the mix.

Enhance the surface appearance with the application of a sealer such as Increte Systems' Clear Seal or Cure Seal

Product Code	Product Color	Etch Aggregate Size	Etch Exposure	
Sure Etch 5	Blue	Sandblast Finish	Micro-Etch	
Sure Etch 25	Peach	Up to 1/4" (6.5mm)	Light	
Sure Etch 100	Gray	1/8" to 1/2" (3-13mm)	Medium	
Sure Etch 200	Pink	5/8" to 1" (16-25mm)	Full-Depth	

Always perform a test under job site conditions to verify correct grade for specific mix design. It is highly recommended that mock-up sample(s) be provided for approval.

### Directions\*

- Shake well before applying.
- Protect adjacent surfaces prior to placing concrete.
- Float or trowel finish placed concrete.
- Apply retarder with a plastic sprayer or roller.
- Coverage rate: 175-300 ft<sup>2</sup>/gallon (4.3-7.4m<sup>2</sup>/l)
- 1-2 hours following application surface is protected from intermittent rain and windy conditions.
- Based on ambient temperature, surface may be rinsed to wash off residue in 4 to 24 hours using a standard garden hose and broom or a high-pressure washer.
- Clean-up with water, product is Eco-Friendly.

\*Data indicated is based on a 6 sack mix.

\*Coverage may vary due to weather/climate conditions.

\*Under certain conditions with specific mixes, same day rinsing may be necessary.

\*For light finishes avoid over-finishing. Do not delay application beyond initial bleeding.



Decorative Concrete Technology



1611 Gann Hwy. Odessa, FL 33556  
813.886.8811 888.752.4626 [www.increte.com](http://www.increte.com)